



Environmental Protection Services Quality Blend Specification

<u>Type of Test</u>	<u>ASTM Method</u>	<u>Typical Values</u>
Color	D 1500	1.0 – 2.0 Max
Corrosive Sulfur	D 1275	Non-Corrosive
Water Content, ppm	D 1533	<50 ppm
Flash Point °F	D 92	280 - 300
Pour Point °F	D 97	-40 Max
Specific Gravity 60/60	D 1298	.880
Viscosity: Saybolt SUS	D 88	
100° F		55 - 65
210° F	D 2161	36
PCB Content (ppm)		< 2 ppm

*For Questions or Samples Contact
Robert J. Creer
Phone - 304-232-1590
Fax - 304-232-1599
Email - rjcreer@epsonline.com*

